



Mortars

Product Data

ADAPHOS 85

ADAPHOS 85 is a wet ready-mixed high alumina bonding mortar with a chemical bonding system. With the unique bonding system, a high bonding strength is developed at lower temperatures (300-600°F) and the high bonding strength continues until a ceramic bonding occurs. **ADAPHOS 85** is primarily used to lay up high alumina brick in ladles and is available in both trowelling and dipping consistencies. It is used in areas where severe service conditions require increased refractoriness to corrosion/erosion from slags.

Refractoriness: Passes ASTM C-199 at 2910°F (1600°C)

P.C.E.: Cone 38+ (ASTM C-24)

Maximum Service Temperature: 3200°F (1760°C)

Joint MOR:

2550°F (1400°C)

600-1000 psi (42-70 kg/cm²)

Chemical Analysis(%):

Al ₂ O ₃	82.7
SiO ₂	12.4
TiO ₂	1.0
Fe ₂ O ₃	0.5
Other	3.4

Screen Sizing: +35 Mesh (Trace)

Standard Packaging: 48-55 lb. pails per pallet

Storage:

ADAPHOS 85 should be stored in a dry place between 32°F (0°C) and 100°F (38°C). For best results use within two months.

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESKO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESKO sales representative or RESKO website to determine you have the current sheet