



# PRODUCT DATA

**Brand Name:** GUIDON

**Description:** GUIDON is a Burned, Fused Grain, Magnesite-Chrome brick

**Physical properties based on ASTM methods where applicable**

**Bulk Density (pcf)**

As Received : 202 (3.24 g/cm<sup>3</sup>)

**Modulus of Rupture (psi)**

At 70°F (21°C) : 870 (61.2 kg/cm<sup>2</sup>)

**Apparent Porosity (%)**

As Received : 14.9

**Typical Chemical Analysis (%)**  
**(Calcined Basis)**

MgO .....	59.2
Cr <sub>2</sub> O <sub>3</sub> .....	20.9
Al <sub>2</sub> O <sub>3</sub> .....	6.4
SiO <sub>2</sub> .....	0.8
Fe <sub>2</sub> O <sub>3</sub> .....	12.0
CaO .....	0.7

Brand Code: 1447

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESOCO PRODUCTS disclaims any express or implied warranties based on this sheet.

10/2/14 is the date that this data sheet was updated. Check with your RESOCO sales representative or RESOCO website at RESCOPRODUCTS.COM to determine if you have the current data sheet.

**Penn Center West, Building 2 - Suite 430, Pittsburgh, PA, 15276 Phone: 888-283-5505**