



PRODUCT DATA

Brand Name: HARKLASE
Description: Burned High Purity Magnesite Brick

Physical properties shown are averages based on standard brick sizes.
ASTM test methods used where applicable

Bulk Density (pcf)
As Received 180 (2.88 g/cm³)

Modulus of Rupture (psi)
At 70°F (21°C) 2410 (168.7 kg/cm²)

Cold Crushing Strength (psi)
At 2700°F (1480°C) 5980 (718.6 kg/cm²)

Permanent Linear Change (%)
After 3140°F (1727°C) -0.1

Apparent Porosity (%)
As Received 17.3

Hot Load Deformation (Using ASTM C-16)
3300°F (1704°C) / 25 psi (1.8 MPa) 2.2%

Typical Chemical Analysis (%)
(Calcined Basis)

Magnesia (MgO)	98.2
Alumina (Al ₂ O ₃)	0.1
Silica (SiO ₂)	0.3
Iron Oxide (Fe ₂ O ₃)	0.4
Lime (CaO)	1.0

Brand Code: 8947

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESKO PRODUCTS disclaims any express or implied warranties based on this sheet.

11/20/17 is the date that this data sheet was updated. Check with your RESKO sales representative or RESKO website to determine you have the current sheet.