

HM 26 LIF

HM 26 LIF IS A FINE GRAIN, GENERAL PURPOSE GUNNING MIX BONDED WITH LOW IRON CEMENT. **HM 26 LIF** CAN BE USED REPAIR AND MAINTENANCE OF COKE OVEN WALLS.

TYPICAL CHEMICAL ANALYSIS (%)	Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO	MgO	TiO ₂	Alk.	Other
	49.3	44.12	1.08	4.2	0.11	1.1	0.42	-----

MATERIAL INSTALLED WEIGHT: 125 (lb/ft³)

SERVICE TEMPERATURE: 2600 °F
 MAXIMUM GRAIN SIZE: 20 Mesh (TYLER)

TEMP. °F	LINEAR CHANGE %	COLD MOR (psi)	COLD CRUSH STRENGTH (psi)	BULK DENSITY (pcf)
300	0 to -.1	450-600	----	125
2000	-.1 to -.3	300-400	----	125
2500	0.2 to 0.3	500-800	----	123

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

11/20/09 is the date that this data sheet was updated. Check with your RESCO/United sales representative or RESCO website to determine you have the current sheet

Brand Code: 3028