

LOW CEMENT GUNNING GRADES

PRODUCT DATA

ProGun LC 40SCG

ProGun LC 40SCG IS A 1500°C LOW CEMENT, ALKALINE RESISTANT GUN MIX WHICH IS IDEALLY GRAIN SIZED TO GIVE EXCELLENT GUNNABILITY, MINIMUM POROSITY AND LINEAR CHANGE WITH MAXIMUM DENSITY AND HIGH FIRED STRENGTHS. DATA SHOWN ARE AVERAGE RESULTS OF TESTS FOLLOWING SAMPLE PREPARATION USING THE GUIDELINES SET FORTH IN ASTM C-903-88, "STANDARD PRACTICES FOR PREPARING REFRACTORY CONCRETES FOR GUNNING".

MAXIMUM SERVICE TEMPERATURE (M.S.T.) (1500°C)

BULK DENSITY

@ 110°C	151 - 156	LBS/FT ³	2418 - 2499	KG/M ³
@ 815°C	150 - 155	LBS/FT ³	2403 - 2483	KG/M ³

COLD CRUSHING STRENGTH

@ 815°C	7500 - 11000	P.S.I.	517 - 759	KG/CM ²
@ 1370°C	7500 - 11000	P.S.I.	517 - 759	KG/CM ²

COLD MODULUS OF RUPTURE

@ 815°C	1000 - 1500	P.S.I.	69 - 103	KG/CM ²
@ 1370°C	1000 - 1500	P.S.I.	69 - 103	KG/CM ²

PERMANENT LINEAR CHANGE

@ 815°C	0.00 TO - 0.40 %
@ 1370°C	0.00 TO - 0.50 %

EROSION LOSS (ASTM C-704)	@ 815°C	Less Than 12 CC
----------------------------------	---------	-----------------

POROSITY @ 815°C 24 %

TYPICAL CHEMICAL ANALYSIS (%)

AL ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO	ZrO ₂	TiO ₂	SiC	ALK
28.0	15.3	0.5	1.6	13.1	1.0	39.3	0.2

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled conditions and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESOCO PRODUCTS disclaims any expressed or implied warranties based on this sheet. 01/08/13 is the date that this data sheet was updated. Check with your RESOCO sales representative or RESOCO website to determine you have the current sheet