



Grains and Raw Materials

Product Data

48 Mesh Grog

Markets: Clay, Pottery & Ceramic Industries

Benefits: Manufactured from high quality fired High Duty and Super Duty Brick Bats

Preparation Method: Raymond Milled and Air Separated

Location: Cedar Heights Clay Division
Post Office Box 295; 3542 St. Route 93
Oak Hill, OH 45656
Phone: 740-682-7794
FAX: 740-682-6438

Pyrometric Cone Equivalent: cone 32 ½ - 33

Typical Screen Analysis:

% Passing 48m 93 - 99

Typical Chemical Analysis(%)

Silica	(SiO ₂)	53.2
Alumina	(Al ₂ O ₃)	41.4
Titania	(TiO ₂)	2.1
Iron Oxide	(Fe ₂ O ₃)	1.4
Lime	(CaO)	0.5
Magnesia	(MgO)	0.3
Alkalies		0.9
Phos	(P ₂ O ₅)	0.2

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/25/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet