



Technical Data

ALUMEX[®] P-85 HS HIGH ALUMINA, HIGH STRENGTH BRICK

PHYSICAL PROPERTIES (ASTM procedures used where applicable)	Bulk Density: (lb/ft ³)	174
	Modulus of Rupture: (lb/in ²)	2,500
	Cold Crushing Strength: (lb/in ²)	14,000
	Apparent Porosity, %:	13.8
	Permanent Linear Change, %: 2910°F (1600°C) & 5 Hours	+0.4
CHEMICAL ANALYSIS (Ignited)	Al ₂ O ₃	79.2
	SiO ₂	10.2
	Fe ₂ O ₃	1.7
	TiO ₂	3.1
	CaO	0.3
	MgO	0.2
	P ₂ O ₅	4.9
	Alkalies	0.4

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESOCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESOCO sales representative or RESOCO website to determine you have the current sheet