



TECHNICAL DATA



DOL-MORTAR-T

LIQUID DOLOMITE MORTAR

<p>FEATURES</p>	<p>High purity sintered dolomite that is sized and blended with non-aqueous liquids to form a troweling consistency mortar for dolomite bricks.</p>										
<p>CHEMICAL ANALYSIS (Ignited)</p>	<table border="0"> <tr> <td>MgO</td> <td>> 36 %</td> </tr> <tr> <td>SiO₂</td> <td>< 1.5 %</td> </tr> <tr> <td>CaO</td> <td>< 61 %</td> </tr> <tr> <td>Al₂O₃ + Mn₃O₄</td> <td>< 1.0 %</td> </tr> <tr> <td>Fe₂O₃</td> <td>< 1.0 %</td> </tr> </table>	MgO	> 36 %	SiO ₂	< 1.5 %	CaO	< 61 %	Al ₂ O ₃ + Mn ₃ O ₄	< 1.0 %	Fe ₂ O ₃	< 1.0 %
MgO	> 36 %										
SiO ₂	< 1.5 %										
CaO	< 61 %										
Al ₂ O ₃ + Mn ₃ O ₄	< 1.0 %										
Fe ₂ O ₃	< 1.0 %										
	<p>PACKAGING AND STORAGE</p> <p>Shipped in ready to use 55 lb., (25 kg) cans. Standard pallet contains 36 cans with a total net weight of 1980 lbs., (900 kg). Remixing for one to two minutes, or warming to room temperature may be required before use. DOL-MORTAR-T may be thinned by adding #2 fuel oil. DO NOT USE WATER. Store pallets in dry and protected area.</p> <p>The chemical and physical properties shown are average values of samples taken from typical production lots. They are subject to reasonable variations and therefore should not be used for specification purposes.</p>										
	<p>The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.</p> <p>RESOCO PRODUCTS disclaims any express or implied warranties based on this sheet.</p> <p>02/05/08 is the date that this data sheet was updated. Check with your RESOCO sales representative or RESOCO website to determine you have the current sheet</p>										