



Technical Data

Guidon

PHYSICAL PROPERTIES (ASTM procedures used where applicable)	<table border="0"> <tr> <td>Bulk Density (lb/ft³):</td> <td>206</td> </tr> <tr> <td>Apparent Porosity, %:</td> <td>13.8</td> </tr> <tr> <td>Cold Crushing(lb/in²): At 70°F (21°C)</td> <td>8480</td> </tr> <tr> <td>Modulus of Rupture(lb/in²): At 70°F (21°C)</td> <td>1600</td> </tr> <tr> <td>At 2700°F (1480°C)</td> <td>570</td> </tr> <tr> <td>Rehheat Test Permanent Linear Change %: After heating at 3100°F (1705°C)</td> <td>+0.2</td> </tr> </table>	Bulk Density (lb/ft ³):	206	Apparent Porosity, %:	13.8	Cold Crushing(lb/in ²): At 70°F (21°C)	8480	Modulus of Rupture(lb/in ²): At 70°F (21°C)	1600	At 2700°F (1480°C)	570	Rehheat Test Permanent Linear Change %: After heating at 3100°F (1705°C)	+0.2
Bulk Density (lb/ft ³):	206												
Apparent Porosity, %:	13.8												
Cold Crushing(lb/in ²): At 70°F (21°C)	8480												
Modulus of Rupture(lb/in ²): At 70°F (21°C)	1600												
At 2700°F (1480°C)	570												
Rehheat Test Permanent Linear Change %: After heating at 3100°F (1705°C)	+0.2												
CHEMICAL ANALYSIS (Ignited)	<table border="0"> <tr> <td>SiO₂</td> <td>0.8 %</td> </tr> <tr> <td>Al₂O₃</td> <td>6.4</td> </tr> <tr> <td>Fe₂O₃</td> <td>12.0</td> </tr> <tr> <td>CaO</td> <td>0.7</td> </tr> <tr> <td>MgO</td> <td>59.2</td> </tr> <tr> <td>Cr₂O₃</td> <td>20.9</td> </tr> </table>	SiO ₂	0.8 %	Al ₂ O ₃	6.4	Fe ₂ O ₃	12.0	CaO	0.7	MgO	59.2	Cr ₂ O ₃	20.9
SiO ₂	0.8 %												
Al ₂ O ₃	6.4												
Fe ₂ O ₃	12.0												
CaO	0.7												
MgO	59.2												
Cr ₂ O ₃	20.9												
	<p>The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.</p> <p>RESOCO PRODUCTS disclaims any express or implied warranties based on this sheet.</p> <p>02/05/08 is the date that this data sheet was updated. Check with your RESOCO sales representative or RESOCO website to determine you have the current sheet</p>												