



Technical Data

LadleMax AMG

RESIN-BONDED, ALUMINA-MAGNESIA-CARBON BRICK

PHYSICAL PROPERTIES (ASTM procedures used where applicable)			<u>Std. Deviation (σ)</u>
	Bulk Density: (lb/ft ³) :	184	(2944 kg/m³)
Modulus of Rupture, (lb/in ²) : at 70°F :	2020	(13.9 MPa)	570 (3.9 MPa)
Apparent Porosity, %:		6.0%	1.7%
Coked Porosity, %:		14.5%	1.5%
Total Carbon, %:		9.3%	n/a
CHEMICAL ANALYSIS (Calcined Basis)	Alumina (Al ₂ O ₃)	82.5%	
	Magnesia (MgO)	8.1	
	Iron Oxide (Fe ₂ O ₃)	1.2	
	Silica (SiO ₂)	5.2	
	Lime (CaO)	0.7	
	Titania (TiO ₂)	2.3	

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

03/25/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet