



# Technical Data

## LARCOBOND® CHROME MORTAR, HEAT-SETTING

FEATURES	A volume stable refractory mortar with good water retention and workability. Suitable for dipping or troweling.
CHEMICAL ANALYSIS (Ignited)	MgO (by Diff.) ..... 55.7 SiO <sub>2</sub> ..... 5.1 CaO ..... 0.8 Al <sub>2</sub> O <sub>3</sub> ..... 8.3 Cr <sub>2</sub> O <sub>3</sub> ..... 18.8 Fe <sub>2</sub> O <sub>3</sub> ..... 11.2 TiO <sub>2</sub> ..... 0.1
AMOUNT REQUIRED	Use 440-490 pounds (200-225 kg) of dry mortar per 1000 9" x 4½" 2½" (228mm x 114mm x 64mm) brick for a 1/16" (1.6mm) troweled joint.
PACKAGING	Standard 55 pound (25 kg) moisture-proof bags

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet