



Product Data

Brand : **MAGNESITE 95**

Preparation

Method : Crushing and Screening of Selective Dead Burned Magnesite.

Manufacturing Location : Resco Canada, Inc.
1330, Route 148
Grenville-sur-la-Rouge, Quebec
Canada

Fractions Available: **Minus 3/4" , Minus 4+10m, BMF65**

Typical Chemical Analysis, %

MgO	95.9%
SiO ₂	1.6
Fe ₂ O ₃	0.6
Al ₂ O ₃	0.5
CaO	1.4

Typical Particle Size Analysis :

	<u>Minus 30 mm</u>	<u>Minus 20 mm</u>
+30 mm	20 % max	
+20 mm		20% max
+5 mm	70 typical	70 typical
-2 mm	20 % max	20 % max

Storage : Magnesite 95 must be stored in a dry place.

Standard

Packaging : Bulk and Bulk bags

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.