



## Product Data

### MAGNESITE 98 3LS BMF 50

**Preparation Method**      Crushing and Screening of Selective Dead Burned Magnesite.

**Manufacturing Location :**      Resco Canada, Inc.  
78 Route 148  
Grenville, Quebec  
J0V 1J0  
Canada

#### **Typical Chemical Analysis, %**

<b>MgO</b>	98.4%
<b>SiO<sub>2</sub></b>	0.25
<b>Fe<sub>2</sub>O<sub>3</sub></b>	0.14
<b>Al<sub>2</sub>O<sub>3</sub></b>	0.12
<b>CaO</b>	1.05
<b>B<sub>2</sub>O<sub>3</sub></b>	0.024

**CaO : SiO<sub>2</sub> :**      4.2

#### **Typical Particle Size Analysis**

+ 28m :	1%
-28m +325 m :	49%
minus 325 m :	50%

**Storage**      Magnesite 98 3LS must be stored in a dry place.

**Standard Packaging**      44 lb. Bags  
55 lb Bags  
2000 lb. Bags  
3000 lb. Bags  
4000 lb. Bags

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.