



# Brick

## Product Data

### NULINE R-20 A

Classification: Magnesia - Carbon Brick Resin Bonded  
20 % Carbon Class  
Strength and Antioxidant Additions

<u>Physical Data: (Typical)</u>	<u>English Units</u>	<u>SI Units</u>
	<u>lb/ft<sup>3</sup></u>	<u>kg/m<sup>3</sup></u>
Bulk Density	177	2,835
Coked Properties		
Density	173	2,771
Porosity, %	10.1	10.1
Residual Carbon, %	18.1	18.1
	<u>lb/in<sup>2</sup></u>	<u>N/mm<sup>2</sup></u>
Crushing Strength		
At 2800°F (1538°C)	2,970	20
Modulus of Rupture		
At 70°F (21°C)	1,580	11
At 2000°F (1093°C)	1,890	13

Chemical Analysis: (Approximate)  
(Calcined Basis)

Silica	(SiO <sub>2</sub> )	0.3 %
Alumina	(Al <sub>2</sub> O <sub>3</sub> )	4.5
Iron Oxide	(Fe <sub>2</sub> O <sub>3</sub> )	0.2
Lime	(CaO)	1.7
Magnesia	(MgO)	93.3

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

2/5/2008 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet