



Brick

Product Data

NULINE 4-95

Classification: Resin Bonded, Magnesia - Carbon Brick
15 % Carbon Class - Part Fused Magnesia
Strength and Antioxidant Additions

<u>Physical Data: (Typical)</u>	<u>English Units</u>	<u>SI Units</u>
	<u>lb/ft³</u>	<u>kg/m³</u>
Bulk Density	181	2,899
Coked Properties		
Density	177	2,835
Porosity, %	11.1	11.1
Total Carbon, %	12.9	12.9
	<u>lb/in²</u>	<u>N/mm²</u>
Crushing Strength		
At 2800°F (1538°C)	4,480	31
Modulus of Rupture		
At 70°F (21°C)	1,930	13
At 2000°F (1093°C)	3,140	22

Chemical Analysis: Approximate
(Calcined Basis)

Silica	(SiO ₂)	0.2 %
Alumina	(Al ₂ O ₃)	8.3
Iron Oxide	(Fe ₂ O ₃)	0.1
Lime	(CaO)	0.8
Magnesia	(MgO)	90.6

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

2/5/2008 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet