



Mortars

Product Data

PACO FIRE CLAY MORTAR

PACO FIRE CLAY MORTAR is a general purpose dry heat setting bonding mortar that is supplied in bags.

Typical Chemical Analysis(%):

Al ₂ O ₃	19.6
SiO ₂	77.7
Fe ₂ O ₃	1.2
TiO ₂	0.8
Alkalies	0.6
MgO	0.1

Size Analysis (% Retained):

4 Mesh	0.1
8 Mesh	1.1
12 Mesh	2.2
20 Mesh	9.7
50 Mesh	36.6
70 Mesh	10.5
Pan	39.8

Maximum Service Temperature: 2300°F

Standard Packaging: 72-55 lb. Bags per pallet

Storage:

PACO FIRE CLAY MORTAR should be stored in a dry place above 32°F (0°C) and below 100°F (38°C).

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet