



## *Fired Shapes*

### *Product Data*

#### **PACO MIX #14**

<u>Pyrometric Cone Equivalent:</u>	cone 26 (2950°F)
<u>Bulk Density:</u>	131-135 lb/ft <sup>3</sup>
<u>Apparent Porosity:</u>	18-21 %
<u>Modulus of Rupture:</u>	800-1000 psi
<u>Cold Crushing Strength:</u>	2500-3500 psi
<u>Strength Retention:</u> After 6 cycles of Air Shock (2250°F to Room Temperature)	
Cold Crushing Strength	90-100%
Modulus of Rupture	55-65 %
<u>Maximum Service Temperature:</u>	2400°F (Flashing)
<u>Coefficient of Thermal Expansion:</u> (Avg.)	
From room temp. to 1425°F	1.9 x 10 <sup>-6</sup> in/in/°F
(From room temp. to 775°C)	(3.3 x 10 <sup>-6</sup> cm/cm/°C)
<u>Long Time Hot Load Test:</u>	
ASTM C 546-67	@2400°F -2.0%
100 hrs., 25 psi	

#### Typical Chemical Analysis(%)

Al <sub>2</sub> O <sub>3</sub>	36.2
SiO <sub>2</sub>	57.4
Fe <sub>2</sub> O <sub>3</sub>	1.6
TiO <sub>2</sub>	1.2
MgO	3.0
CaO	0.1
K <sub>2</sub> O	0.3
Na <sub>2</sub> O	0.2

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet