



PRODUCT DATA

Brand Name: **PROGUN 26LI - DS**

Description: This product is a dust suppressed version of Progun 26LI. This gun mix also features low rebounds and improved gunning characteristics.

Maximum Service Temperature **2600°F (1427°C)**

Typical Water Required for Mixing :
For Predampening **2 to 3%**

Bulk Density (lb/ft³)

After 230°F (105°C)	134	(2144 kg/m³)
After 1500°F (816°C)	128	(2048 kg/m³)

Cold Crushing Strength (lb/in²)

After 220°F (105°C)	6500	(455 kg/cm²)
After 1500°F (816°C)	3000	(210 kg/cm²)

Permanent Linear Change (%)
After 1500°F (815 °C) **-0.4 to +0.3**

Typical Chemical Analysis (%)

Al ₂ O ₃	44.9 %
SiO ₂	42.8
Fe ₂ O ₃	1.3
TiO ₂	1.8
CaO	7.7
MgO	0.4
Alkalies	1.1

Standard Packaging: **55 lb. bags; 72 bags per pallet**

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.