



# PRODUCT DATA

## ProGun LC 30GM LOW CEMENT GUN MIX

Recommended Service Temperature Limit ..... 3000°F  
 Water Required for Mixing ..... At Nozzle (1)  
 Material Required Per Ft<sup>3</sup>..... 142 lbs (2)  
 Packaging..... 55 lb bag

TEMPERATURE (°F)	BULK DENSITY (lb/ft <sup>3</sup> )	LINEAR CHANGE (%)	MODULUS OF RUPTURE (lb/in <sup>2</sup> )	COLD CRUSH STRENGTH (lb/in <sup>2</sup> )	APPARENT POROSITY (%)	ABRASION LOSS (cm <sup>3</sup> )
220	142-147	-----	1200-1600	8000-10000	11 - 15	5-9
1500	139-144	-0.4 to 0.0	1100-1500	4000- 6000	18 - 21	8-10
2910	131-135	0.0 to 1.3	1800-2200	14500-18000	6 - 10	-----

### CHEMICAL ANALYSIS: (Ignited)

Al <sub>2</sub> O <sub>3</sub>	.....	59.0%
SiO <sub>2</sub>	.....	33.5
Fe <sub>2</sub> O <sub>3</sub>	.....	1.2
TiO <sub>2</sub>	.....	2.0
CaO	.....	2.4
MgO	.....	0.4
Alkalies	.....	1.5

- (1) Predampening at 2.5-3.5% is recommended to minimize dusting and decrease rebound.  
 (2) This value does not include rebound.

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESKO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/29/08 is the date that this data sheet was updated. Check with your RESKO sales representative or RESKO website to determine you have the current sheet.