



Insulating Castables

Cast Data

QUIKLITE 8

QUIKLITE 8 is a medium weight insulating castable formulated for a rapid heatup, without using the traditional ramp-and-hold heating schedule. This material can be used as an original lining material or as a replacement for refractory ceramic fiber. **QUIKLITE 8** can be installed by casting or gunning.

Maximum Service Temperature: 2800°F (1540°C)

Bulk Density:
After 1500°F (815°C): 88 pcf (1408 kg/m³)

Cold Crushing Strength:
After 1500°F (815°C) 600-1400 psi (42 - 98 kg/cm²)

Modulus of Rupture:
After 1500°F (815°C) 150-300 psi (11-21 kg/cm²)

Permanent Linear Change(%):
After 1500°F (815°C) -0.1 to +0.2

Thermal Conductivity or "K" Factor:

Mean Temp.	BTU/ft ² /Hr/°F/in	W/mK
500°F (260°C)	2.50	0.36
1000°F (540°C)	2.70	0.39
1500°F (815°C)	2.85	0.41
2000°F (1095°C)	3.05	0.44

Typical Chemical Analysis (%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO	MgO	TiO ₂	Alkalies
49.0	43.2	0.5	5.6	0.3	0.5	0.9

Standard Packaging: 50-50 lb. bags per pallet (bulk packaging available)

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/29/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet

GUNNED DATA SHOWN ON PAGE 2



Insulating Castables – page 2

Gunned Data

QUIKLITE 8

GUNNED DATA

Data shown are the average results of tests following the guidelines set forth in ASTM C-903, "Preparing Refractory Castable Specimens by Cold Gunning." Results will vary subject to normal variations in manufacturing, testing and installation procedures in the field.

<u>Maximum Service Temperature:</u>	2800°F (1540°C)
<u>Bulk Density:</u> After 1500°F (815°C)	95-105 pcf (1520-1260 kg/m ³)
<u>Cold Crushing Strength:</u> After 1500°F (815°C)	900-1300 psi (63-91 kg/cm ²)
<u>Modulus of Rupture:</u> After 1500°F (815°C)	300-500 psi (21-35 kg/cm ²)
<u>Permanent Linear Change(%):</u> After 1500°F (815°C)	-0.1 to +0.2