



Mortars

Product Data

RESCO BLOCK VENEERING CEMENT

RESCO BLOCK VENEERING CEMENT is a high temperature, air-setting bonding mortar specially blended to give proper consistency for applying **PYRO BLOC**.

Refractoriness: Passes ASTM C-199 at 2910°F (1600°C)

P.C.E.: Cone 29 (ASTM C-24)

Maximum Service Temperature: 3000°F (1650°C)

Joint MOR:

220°F (105°C)

2550°F (1400°C)

900-1200 psi (63-84 kg/cm²)

1500-2000 psi (105-140 kg/cm²)

Chemical Analysis(%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	Other
42.4	52.2	0.5	1.1	3.8

Standard Packaging: 50 lb. pails

Storage:

RESCO BLOCK VENEERING CEMENT should be stored in a dry place above 32°F (0°C) and below 100°F (38°C). For best results use within two months.

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet