



TECHNICAL DATA



RG50-DOL

RESIN BONDED, MAGNESITE AND CARBON ENRICHED,
DOLOMITE BRICK

FEATURES	High purity sintered dolomite that is sized, blended with magnesite, a resin and carbon system pressed and heated to remove volatiles and create good ambient temperature strength. RG50-DOL is paraffin dipped to resist hydration after pallet is opened. RG50-DOL is a premium quality refractory for more aggressive wear areas in slag lines and impact pads of															
PHYSICAL PROPERTIES (ASTM procedures used where applicable)	<table style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 60%;"></th> <th style="width: 20%; text-align: center;"><u>g/cm³</u></th> <th style="width: 20%; text-align: center;"><u>lb/ft³</u></th> </tr> </thead> <tbody> <tr> <td>Bulk Density:</td> <td style="text-align: center;">2.78-2.92</td> <td style="text-align: center;">174-182</td> </tr> <tr> <td>Apparent Porosity, %:</td> <td colspan="2" style="text-align: center;">5-9</td> </tr> <tr> <td></td> <td style="text-align: center;"><u>N/mm²</u></td> <td style="text-align: center;"><u>lb/in²</u></td> </tr> <tr> <td>Cold Crushing Strength:</td> <td style="text-align: center;">>24</td> <td style="text-align: center;">>3480</td> </tr> </tbody> </table>		<u>g/cm³</u>	<u>lb/ft³</u>	Bulk Density:	2.78-2.92	174-182	Apparent Porosity, %:	5-9			<u>N/mm²</u>	<u>lb/in²</u>	Cold Crushing Strength:	>24	>3480
	<u>g/cm³</u>	<u>lb/ft³</u>														
Bulk Density:	2.78-2.92	174-182														
Apparent Porosity, %:	5-9															
	<u>N/mm²</u>	<u>lb/in²</u>														
Cold Crushing Strength:	>24	>3480														
CHEMICAL ANALYSIS (Ignited)	<table style="width: 100%; border-collapse: collapse;"> <tbody> <tr> <td style="width: 60%;">MgO (Diff.)</td> <td style="width: 40%; text-align: right;">> 65.0 %</td> </tr> <tr> <td>SiO₂</td> <td style="text-align: right;">< 1.0 %</td> </tr> <tr> <td>CaO</td> <td style="text-align: right;">< 32.0 %</td> </tr> <tr> <td>Al₂O₃ + Mn₃O₄</td> <td style="text-align: right;">< 1.0 %</td> </tr> <tr> <td>Fe₂O₃</td> <td style="text-align: right;">< 1.0 %</td> </tr> <tr> <td>Retained Carbon</td> <td style="text-align: right;">> 5 %</td> </tr> </tbody> </table>	MgO (Diff.)	> 65.0 %	SiO ₂	< 1.0 %	CaO	< 32.0 %	Al ₂ O ₃ + Mn ₃ O ₄	< 1.0 %	Fe ₂ O ₃	< 1.0 %	Retained Carbon	> 5 %			
MgO (Diff.)	> 65.0 %															
SiO ₂	< 1.0 %															
CaO	< 32.0 %															
Al ₂ O ₃ + Mn ₃ O ₄	< 1.0 %															
Fe ₂ O ₃	< 1.0 %															
Retained Carbon	> 5 %															
	<p style="text-align: center;">PACKAGING AND STORAGE</p> <p>Standard full pallets are packaged in vacuum sealed ALUVAC foil for optimum shelf life. Care should be taken to prevent ALUVAC damage. Store pallets in a dry protected area.</p>															
	<p>The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.</p> <p>RESOCO PRODUCTS disclaims any express or implied warranties based on this sheet.</p> <p>02/05/08 is the date that this data sheet was updated. Check with your RESOCO sales representative or RESOCO website to determine you have the current sheet</p>															