



Panel Mixes

Product Data

RESCOCAST 3A PANEL MIX

RESCOCAST 3A is a lightweight, low iron, insulating panel mix which has a service limit temperature of 2500°F. It is used primarily where reducing atmospheres may be present.

Maximum Service Temperature: 2500°F (1370°C)

Bulk Density: 62 lbs/ft³ (992 kg/m³)

Cold Crushing Strength:

1500°F (815°C)	300-450 psi (21-32 kg/cm ²)
2000°F (1095°C)	300-450 psi (21-32 kg/cm ²)
2500°F (1370°C)	400-550 psi (28-39 kg/cm ²)

Modulus Of Rupture:

1500°F (815°C)	100-200 psi (7-14 kg/cm ²)
2000°F (1095°C)	100-200 psi (7-14 kg/cm ²)
2500°F (1370°C)	150-250 psi (11-18 kg/cm ²)

Permanent Linear Change(%):

1500°F (815°C)	-0.1 to -0.5
2000°F (1095°C)	-0.4 to -0.9
2500°F (1370°C)	-0.8 to -1.3

Porosity(%): 50

Conductivity or "K" Factor:

Mean Temp.	BTU/ft ² /Hr/°F/in	W/mK
500°F (260°C)	1.40	0.20
1000°F (540°C)	1.60	0.23
1500°F (815°C)	1.70	0.25
2000°F (1095°C)	1.85	0.27

Typical Chemical Analysis(%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO	MgO	Alkalies	TiO ₂
41.9	44.6	1.0	10.4	0.1	1.2	0.8

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/28/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet

Penn Center West, Building Two - Suite 430, Pittsburgh, PA., 15276 Phone: 888-283-5505 • Fax 412-294-1080
 14801 South Anson Ave., Santa Fe Springs, Calif., 90670 Phone: 562-802-2463 • Fax: 562-802-0315
www.rescoproducts.com