



Plastics and Ramming Mixes

Product Data

RESCORAM 70 BLUE

RESCORAM 70 BLUE is a mullite, phosphate-bonded plastic material that is used throughout the metals, power, cement, and lime producing industries. Its chemical bond develops high strength at lower temperatures. This property makes it ideal for application where there is insufficient heat to develop the ceramic bond required in heat-setting plastics. This product is designed to resist alkali attack.

Maximum Service Temperature: 3100°F (1704°C)

Bulk Density: (As installed) 165 lbs/ft³ (2640 kg/m³)

Modulus of Rupture:

1500°F (815°C)	1325 psi (93kg/cm ²)
2500°F (1370°C)	2050 psi (143 kg/cm ²)
2910°F (1600°C)	2000 psi (140 kg/cm ²)

Drying Shrinkage (green - 220°F): 1.1 %

Permanent Linear Change (%):

(220°F to fired)

1500°F (815°C)	+ 0.02
2500°F (1370°C)	- 0.38
2910°F (1600°C)	+0.68

Conductivity or "K" Factor:

Mean Temp.	BTU/ft ² /Hr/°F/in	W/mK
1000°F (540°C)	9.2	1.47
1500°F (815°C)	9.0	1.51
2000°F (1095°C)	8.8	1.54

Erosion Loss: ASTM C-704 Less than 13 cc
(Typical: 10 –12 cc)

Typical Chemical Analysis(%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	CaO	MgO	Alkalies	P ₂ O ₅
72.0	20.6	1.0	1.8	0.1	0.2	0.4	3.9

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet