



PRODUCT DATA

Brand Name: RESCOSET 85 AS

Description: Wet, Air Setting, 85% Alumina Bonding Mortar with a low silica content

Maximum Service Temperature 3200°F (1760°C)

Amount Required

For 1000 - 9" straight brick: 400 to 450 lb

Typical Chemical Analysis (%)

Al ₂ O ₃	85.7%
SiO ₂	10.5
Fe ₂ O ₃	0.6
TiO ₂	1.4
CaO	0.1
MgO	0.1
Alkalies	1.6

Standard Packaging: 50 lb plastic pail

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

Penn Center West, Building 2 - Suite 430, Pittsburgh, PA, 15276 Phone: 888-283-5505