



TECHNICAL DATA

RESCOSET Chrome Mortar

Recommended Service Temperature Limit	3200°F
Refractoriness Classification.....	Special
Amount Required.....	
:To Lay 1,000 9" Straight Brick.....	400 - 450 lb
Packaging.....	55 lb bag

CHEMICAL ANALYSIS: (Ignited)

Al ₂ O ₃	14.1
SiO ₂	11.9
Cr ₂ O	38.2
Fe ₂ O	23.8
TiO ₂	0.1
CaO	0.1
MgO	7.9
Alkalies	3.1
P ₂ O ₅	0.8

This data represents average properties obtained from commercial production lots and should not be considered guaranteed specifications. RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

1/22/2010 is the date this data sheet was published. Check with your RESCO sales office to make sure you have a current data sheet, since this technical data may have changed.