



Mortars

Product Data

S. D. LAYING MIX

S. D. LAYING MIX is a general purpose dry air-setting bonding mortar. Primary uses include kiln car refractories leveling and positioning.

Maximum Grain Size: 20 Mesh

Max. Service Temp: 2200°F (1204°C)

Chemical Analysis(%):

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	Alkalies
22.5	75.5	0.5	0.4	1.1

Standard Packaging: 42 - 75 lb. bags per pallet

Storage:

S. D. LAYING MIX should be stored in a dry place above 32°F (0°C) and below 100°F (38°C).

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/05/08 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet