



Technical Data

SENECA 80 HIGH ALUMINA BRICK

PHYSICAL PROPERTIES (ASTM procedures used where applicable)			<u>Std. Deviation (σ)</u>
	Bulk Density: (lb/ft ³) :	172	(2752 kg/m³)
Modulus of Rupture: (lb/in ²) :	1800	(126 kg/cm²)	390 (27.3 kg/cm²)
Cold Crushing Strength: (lb/in ²)	10,200	(714 kg/cm²)	n/a
Apparent Porosity, %:		16.0%	1.1%
Permanent Linear Change, % 2910°F (1600°C) & 5 Hours :		+ 2.0 %	n/a
CHEMICAL ANALYSIS (Calcined Basis)	Alumina (Al ₂ O ₃)	78.7	
	Silica (SiO ₂)	14.6	
	Iron Oxide (Fe ₂ O ₃)	1.5	
	Titania (TiO ₂)	3.1	
	Lime (CaO)	0.4	
	Magnesia (MgO)	0.3	
	Phosphorus Pentoxide (P ₂ O ₅)	0.9	
Alkalies	0.5		

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESOCO PRODUCTS disclaims any express or implied warranties based on this sheet.

03/25/08 is the date that this data sheet was updated. Check with your RESOCO sales representative or RESOCO website to determine you have the current sheet