



TECHNICAL DATA



Z-DOL

BURNED, SPALL RESISTANT DOLOMITE BRICK for CEMENT KILNS

<p>FEATURES</p>	<p>High purity sintered dolomite that is sized, blended with zirconia, pressed into a brick shape for rotary kilns, then fired in a high temperature tunnel kiln to create a strong ceramically bonded brick. Z-DOL is a premium quality, spall resistant refractory for use in the burning zone of a rotary cement kiln.</p>																											
<p>PHYSICAL PROPERTIES (ASTM procedures used where applicable)</p>	<table style="width: 100%; border-collapse: collapse;"> <tr> <td></td> <td style="text-align: center;"><u>g/cm³</u></td> <td style="text-align: center;"><u>lb/ft³</u></td> </tr> <tr> <td style="text-align: right;">Bulk Density:</td> <td style="text-align: center;">2.80-2.90</td> <td style="text-align: center;">175-181</td> </tr> <tr> <td style="text-align: right;">Apparent Porosity, %:</td> <td colspan="2" style="text-align: center;">15-19</td> </tr> <tr> <td></td> <td style="text-align: center;"><u>N/mm²</u></td> <td style="text-align: center;"><u>lb/in²</u></td> </tr> <tr> <td style="text-align: right;">Cold Crushing Strength:</td> <td style="text-align: center;">>40</td> <td style="text-align: center;">>5800</td> </tr> <tr> <td></td> <td style="text-align: center;"><u>BTU/(ft², hr, °F, in)</u></td> <td style="text-align: center;"><u>W/mK</u></td> </tr> <tr> <td style="text-align: right;">Thermal Conductivity:</td> <td></td> <td></td> </tr> <tr> <td style="text-align: right;">At 1242 °F (700 °C)</td> <td style="text-align: center;">18.0</td> <td style="text-align: center;">2.6</td> </tr> <tr> <td style="text-align: right;">At 1832 °F (1000 °C)</td> <td style="text-align: center;">16.6</td> <td style="text-align: center;">2.4</td> </tr> </table>		<u>g/cm³</u>	<u>lb/ft³</u>	Bulk Density:	2.80-2.90	175-181	Apparent Porosity, %:	15-19			<u>N/mm²</u>	<u>lb/in²</u>	Cold Crushing Strength:	>40	>5800		<u>BTU/(ft², hr, °F, in)</u>	<u>W/mK</u>	Thermal Conductivity:			At 1242 °F (700 °C)	18.0	2.6	At 1832 °F (1000 °C)	16.6	2.4
	<u>g/cm³</u>	<u>lb/ft³</u>																										
Bulk Density:	2.80-2.90	175-181																										
Apparent Porosity, %:	15-19																											
	<u>N/mm²</u>	<u>lb/in²</u>																										
Cold Crushing Strength:	>40	>5800																										
	<u>BTU/(ft², hr, °F, in)</u>	<u>W/mK</u>																										
Thermal Conductivity:																												
At 1242 °F (700 °C)	18.0	2.6																										
At 1832 °F (1000 °C)	16.6	2.4																										
<p>CHEMICAL ANALYSIS (Ignited)</p>	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="text-align: right;">MgO (Diff.)</td> <td style="text-align: right;">> 37 %</td> </tr> <tr> <td style="text-align: right;">SiO₂</td> <td style="text-align: right;">< 1.2 %</td> </tr> <tr> <td style="text-align: right;">CaO</td> <td style="text-align: right;">< 58 %</td> </tr> <tr> <td style="text-align: right;">Al₂O₃ + Mn₃O₄</td> <td style="text-align: right;">< 0.8 %</td> </tr> <tr> <td style="text-align: right;">Fe₂O₃</td> <td style="text-align: right;">< 1.3 %</td> </tr> <tr> <td style="text-align: right;">ZrO₂</td> <td style="text-align: right;">1-2%</td> </tr> </table>	MgO (Diff.)	> 37 %	SiO ₂	< 1.2 %	CaO	< 58 %	Al ₂ O ₃ + Mn ₃ O ₄	< 0.8 %	Fe ₂ O ₃	< 1.3 %	ZrO ₂	1-2%															
MgO (Diff.)	> 37 %																											
SiO ₂	< 1.2 %																											
CaO	< 58 %																											
Al ₂ O ₃ + Mn ₃ O ₄	< 0.8 %																											
Fe ₂ O ₃	< 1.3 %																											
ZrO ₂	1-2%																											
	<p style="text-align: center;">PACKAGING AND STORAGE</p> <p>Standard full pallets are packaged in vacuum sealed ALUVAC foil for optimum shelf life. Care should be taken to prevent ALUVAC damage. Store pallets in a dry protected area.</p>																											
	<p>The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.</p> <p>RESKO PRODUCTS disclaims any express or implied warranties based on this sheet.</p> <p>02/05/08 is the date that this data sheet was updated. Check with your RESKO sales representative or RESKO website to determine you have the current sheet</p>																											