



TECHNICAL DATA



ZLP-DOL

BURNED, SPALL RESISTANT DOLOMITE BRICK for CEMENT KILNS

<p>FEATURES</p>	<p>High purity sintered dolomite that is critically sized, blended with zirconia, pressed into a brick shape for rotary kilns, then fired in a high temperature tunnel kiln to create a strong ceramically bonded brick. ZLP-DOL is a premium quality, spall resistant refractory for use in burning zones that experience chemical attack.</p>															
<p>PHYSICAL PROPERTIES (ASTM procedures used where applicable)</p>	<table style="width: 100%; border-collapse: collapse;"> <tr> <td></td> <td style="text-align: center;"><u>g/cm³</u></td> <td style="text-align: center;"><u>lb/ft³</u></td> </tr> <tr> <td style="text-align: right;">Bulk Density:</td> <td style="text-align: center;">2.73-2.95</td> <td style="text-align: center;">170-184</td> </tr> <tr> <td style="text-align: right;">Apparent Porosity, %:</td> <td colspan="2" style="text-align: center;">15-19</td> </tr> <tr> <td></td> <td style="text-align: center;"><u>N/mm²</u></td> <td style="text-align: center;"><u>lb/in²</u></td> </tr> <tr> <td style="text-align: right;">Cold Crushing Strength:</td> <td style="text-align: center;">>25</td> <td style="text-align: center;">>3600</td> </tr> </table>		<u>g/cm³</u>	<u>lb/ft³</u>	Bulk Density:	2.73-2.95	170-184	Apparent Porosity, %:	15-19			<u>N/mm²</u>	<u>lb/in²</u>	Cold Crushing Strength:	>25	>3600
	<u>g/cm³</u>	<u>lb/ft³</u>														
Bulk Density:	2.73-2.95	170-184														
Apparent Porosity, %:	15-19															
	<u>N/mm²</u>	<u>lb/in²</u>														
Cold Crushing Strength:	>25	>3600														
<p>CHEMICAL ANALYSIS (Ignited)</p>	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="text-align: right;">MgO (Diff.)</td> <td style="text-align: right;">> 37.0 %</td> </tr> <tr> <td style="text-align: right;">SiO₂</td> <td style="text-align: right;">< 1.2 %</td> </tr> <tr> <td style="text-align: right;">CaO</td> <td style="text-align: right;">< 58.0 %</td> </tr> <tr> <td style="text-align: right;">Al₂O₃ + Mn₃O₄</td> <td style="text-align: right;">< 0.8 %</td> </tr> <tr> <td style="text-align: right;">Fe₂O₃</td> <td style="text-align: right;">< 1.3 %</td> </tr> <tr> <td style="text-align: right;">ZrO₂</td> <td style="text-align: right;">1-2 %</td> </tr> </table>	MgO (Diff.)	> 37.0 %	SiO ₂	< 1.2 %	CaO	< 58.0 %	Al ₂ O ₃ + Mn ₃ O ₄	< 0.8 %	Fe ₂ O ₃	< 1.3 %	ZrO ₂	1-2 %			
MgO (Diff.)	> 37.0 %															
SiO ₂	< 1.2 %															
CaO	< 58.0 %															
Al ₂ O ₃ + Mn ₃ O ₄	< 0.8 %															
Fe ₂ O ₃	< 1.3 %															
ZrO ₂	1-2 %															
	<p style="text-align: center;">PACKAGING AND STORAGE</p> <p>Standard full pallets are packaged in vacuum sealed ALUVAC foil for optimum shelf life. Care should be taken to prevent ALUVAC damage. Store pallets in a dry protected area.</p>															
	<p>The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.</p> <p>RESOCO PRODUCTS disclaims any express or implied warranties based on this sheet.</p> <p>02/05/08 is the date that this data sheet was updated. Check with your RESOCO sales representative or RESOCO website to determine you have the current sheet</p>															