



TECHNICAL DATA INSULATING CASTABLES WATER TABLE

Product	Cast Water Range (%)		Gunitite Pre-Damp Water (%)		Pumpcast Water Range (%)	
CASTABLE #16	95.0	100.0	8.3	10.4	*	*
I-R-C 20	42.0	48.0	*	*	*	*
I-R-C 20-G	48.0	52.0	8.0	10.0	*	*
I-R-C 22	43.0	47.0	11.0	13.0	*	*
I-R-C 22-G	43	47	8.0	10.0	*	*
I-R-C 24-LI	42.0	46.0	12.0	18.0	*	*
I-R-C 24-LI G	*	*	8.0	10.0	*	*
I-R-C 25	32.0	36.0	*	*	*	*
I-R-C 25-LI	25.0	32.0	*	*	*	*
I-R-C 25-LI G	27.0	34.0	4.0	7.0	*	*
I-R-C 26-LI	22.0	27.0	*	*	*	*
I-R-C 29-LI	19.0	24.0	*	*	*	*
KC MIX	35.0	38.0	8.3	10.4	*	*
LH-14	24.0	27.0	8.3	10.4	*	*
LHP-124	34.0	39.0	8.3	10.4	*	*
LHV-124	42.0	46.0	8.3	10.4	*	*
PUROLITE-22	54.0	58.0	*	*	*	*
PUROLITE-30	25.0	30.0	6.0	8.0	*	*
RESCOCAST 3	35.0	40.0	8.3	10.4	*	*
RESCOCAST 3 QT	35.0	40.0	8.3	10.4	*	*
RESCOCAST 3 PC	35	38	*	*	38	40
RESCOCAST 3 PC QT	35	38	*	*	38	40
RESCOCAST 3-20	152.0	165.0	16.6	25.0	*	*
RESCOCAST 3-20H	120.0	130.0	16.6	25.0	*	*
RESCOCAST 3-20R	125.0	132.0	16.6	25.0	*	*
RESCOCAST 3-35	79.0	82.0	11.9	17.8	*	*
RESCOCAST 3-35P	120.0	125.0	16.6	25.0	*	*
RESCOCAST 3-35P QT	120.0	125.0	16.6	25.0	*	*
RESCOCAST 3-35PC	87.0	92.0	*	*	87.0	92.0
RESCOCAST 3A	34.0	37.0	9.2	11.6	*	*
RESCOCAST 3A-DS	34.0	37.0	9.2	11.6	*	*
RESCOCAST 3APC	38.0	42.0	*	*	38.0	42.0
RESCOCAST 3B	55.0	59.0	10.4	13.0	*	*
RESCOCAST 3E	36.0	39.0	9.2	11.6	*	*
RESCOCAST 3EPC	38.0	40.0	*	*	40.0	42.0
RESCOCAST 4LI	34.0	37.0	8.3	10.4	*	*
RESCOCAST 6	27.0	30.0	6.9	8.7	*	*
RESCOCAST 6 PC	25	27	*	*	27	30
RESCOCAST 6A	27.0	30.0	6.9	8.7	*	*
RESCOCAST 6C	25.0	27.0	*	*	*	*
RESCOCAST 7	27.0	30.0	8.3	10.4	*	*
RESCOCAST 8	22.0	25.0	8.3	10.4	*	*
RESCOCAST 8 QT	22.0	25.0	8.3	10.4	*	*
RESCOCAST 9	22.0	24.0	8.3	10.4	*	*
RESCOCAST 9LI	22.0	24.0	8.3	10.4	*	*
RESCOCAST 9LI QT	22.0	24.0	8.3	10.4	*	*
RESCOCAST 9LI-PC	23.0	25.0	*	*	23.0	25.0

* NOT A RECOMMENDED INSTALLATION METHOD