



TECHNICAL DATA

CONVENTIONAL CASTABLES

WATER TABLE

Product	Cast Water Range (%)		Guniting Pre-Damp (%)		Pumpcast Water Range (%)		Shotcrete Water Range (%)	
CLEAVERCAST	10.0	11.0	*	*	*	*	*	*
EZ CAST 2700	4.5	6.0	*	*	6.5	8.5	*	*
EZ CAST 2800	4.5	6.0	*	*	7.0	8.3	*	*
EZ CAST 40-AL	4.5	6.0	*	*	6.5	8.5	*	*
EZ CAST LO-ERODE	5.0	6.0	*	*	7.0	8.0	*	*
EZ ³ 2700	4.5	6.0	*	*	7.0	8.5	6.5	7.5
EZ ³ 2800	5.0	6.5	*	*	7.0	8.3	6.5	8.0
EZ ³ 2800-BF	5.0	6.5	*	*	7.0	8.3	6.5	8.0
EZ ³ LO-ERODE	5.3	6.3	*	*	7.0	8.0	6.5	7.5
FURNA ³ 40	4.5	6.0	*	*	7.0	8.5	6.5	7.5
FURNARAM	16.0	19.0	*	*	*	*	*	*
FURNASCREE COARSE	14.0	17.0	*	*	*	*	*	*
FURNASCREE TROWEL MIX	21.0	22.0	*	*	*	*	*	*
FURNASCREE	15.0	20.0	*	*	*	*	*	*
HI-STRENGTH 25	11.0	14.0	*	*	*	*	*	*
HI-STRENGTH 26-LI	11.0	14.0	*	*	*	*	*	*
HI-STRENGTH 28-LI	9.0	12.0	*	*	*	*	*	*
HI-STRENGTH COARSE 23	10.0	13.0	*	*	*	*	*	*
HI-STRENGTH COARSE 25-LI	9.5	13.0	*	*	*	*	*	*
HI-STRENGTH COARSE 27	8.5	11.0	*	*	*	*	*	*
LADLELINE	7.0	9.0	*	*	*	*	*	*
LO-ERODE	9.0	12.0	*	*	*	*	*	*
ProCAST 90-10	5.0	5.5	*	*	*	*	*	*
ProCAST 96-GR	8.0	9.0	*	*	*	*	*	*
PUROCAST N	8.0	10.0	*	*	*	*	*	*
PUROCRETE	8.5	11.0	*	*	*	*	*	*
PUROTAB COARSE	6.0	7.5	*	*	*	*	*	*
PUROTAB	7.5	10.5	*	*	*	*	*	*
PYROCAST 3000C	9.5	11.0	*	*	*	*	*	*
PYROCAST ARC	13.0	14.0	*	*	*	*	*	*
PYROCAST FPM-C	13.0	15.0	*	*	*	*	*	*
RESCOCAST 15	12.0	14.0	1.9	3.8	*	*	*	*
RESCOCAST 15A	12.0	14.0	*	*	*	*	*	*
RESCOCAST 15GM	12.0	14.0	1.9	3.8	13.0	15.0	13.0	15.0
RESCOCAST 15HT	11.0	13.0	1.9	3.8	*	*	*	*
RESCOCAST 15HT Coarse	12.0	14.0	1.9	3.8	*	*	*	*
RESCOCAST 17	7.0	10.5	1.9	3.8	*	*	*	*
RESCOCAST 45	20.0	26.0	*	*	20.0	26.0	*	*
SAKONITE	13.0	16.0	*	*	*	*	*	*

* NOT A RECOMMENDED INSTALLATION METHOD