

LOW CEMENT GUNNING GRADES

PRODUCT DATA

ProGun LC 80SCG

ProGun LC 80SCG is an 80% SiC castable that uses **low cement** binder technology with the gunite installation method. Its low porosity, excellent abrasion resistance and high heat transfer value make this product an excellent choice for the tube walls in the combustion zones of power generating units. The high heat transfer characteristic of the SiC reduces surface slagging and alkali build-up, thereby, improving the operating efficiency of your unit. Data shown are average results of tests following the guidelines set forth in ASTM C-903-70 "Preparing Refractory Concrete Specimens by Cold Gunning".

Maximum Service Temperature:		2800°F (1540°C)				
Bulk Density: 220°F (105°C 1700°F (927°C	2)			ft ³ (2352-2432 ft ³ (2288-2368		
<u>Cold Crushing Strength:</u> 1700°F (927°C)		8000-11000 psi (560-770 kg/cm ²)				
Modulus of Rupture: 1700°F (927°C)		2000-3000 psi (140-210 kg/cm ²)				
<u>Permanent Li</u> 1700°F (927°C		<u>e(%):</u>	-0.1 to -0.4	Ļ		
<u>Erosion Loss:</u> 1700°F (927°C)			Less than 10 cc (Typical 7 cc to 8 cc)			
Conductivity Mean Temp.	or "K" Fact	<u>or:</u>	BTU/ft ² /HR/ºF/in		W/mK	
(713°C)			50		7.22	
Typical Chemical Analysis(%):SiCAl2O3SiO2			Fe ₂ O ₃	CaO	TiO ₂	Other
79.8	8.7	9.2	0.2	2.0	TR	0.1

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled conditions and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice. RESCO PRODUCTS disclaims any expressed or implied warranties based on this sheet. 01/08/13 is the date that this data

sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet

