

## SELF FLOW CASTABLES

#### PRODUCT DATA

# **SUREFLOW 60LC**

SUREFLOW 60LC IS A 1650°C LOW CEMENT CASTABLE WHICH REQUIRES NO VIBRATION, RODDING OR TAMPING TO INSTALL. THIS "FREE FLOWING" OR "SELF FLOWING" CASTABLE GIVES SUPER HIGH STRENGTHS, ABRASION RESISTANCE AND VOLUME STABILITY.

THE DATA SHOWN IS BASED ON MATERIAL PREPARED TO A CONVENTIONAL FOLD CONSISTANCY AND ALLOWED TO SELF-FLOW INTO FORMWORK WITHOUT VIBRATION OR TAMPING.

MAXIMUM SERVICE TEMPERATURE (M.S.T.) 1650°C

#### BULK DENSITY

@ 815°C 144 - 153 LBS/FT<sup>3</sup> 2300 - 2450 KG/M<sup>3</sup>

#### COLD CRUSHING STRENGTH

@ 815°C	8000 - 15000	P.S.I.	560 - 1050	KG/CM <sup>2</sup>
@ M.S.T.	9000 - 16000	P.S.I.	630 - 1120	KG/CM <sup>2</sup>

#### PERMANENT LINEAR CHANGE

@ 815°C - 0.00 TO - 0.40 %

## EROSION LOSS (ASTM C-704)

### @ 815°C 8 CC MAX

#### CONDUCTIVITY OR "K" FACTOR

<u>MEAN TEMP</u> @ 540°C @ 1095°C	BTU/FT <sup>2</sup> /Hr/ <sup>°</sup> F/in 9.5 10.5				W/mK 1.33 1.47			
TYPICAL CHEMICAL ANALYSIS (%)								
<b>AL</b> 2O3	SiO2	Fe 2 0 3	CaO	MgO	<b>TiO</b> ₂	AlK		
60.0	33.7	0.9	2.0	0.3	1.3	0.3		

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled conditions and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice. RESCO PRODUCTS disclaims any expressed or implied warranties based on this sheet. 01/08/13 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet

