

## SUREFLOW 80 SC DC

*SUREFLOW 80 SC DC IS A SILICON CARBIDE BASED LOW CEMENT CASTABLE SPECIFICALLY DESIGNED FOR INSTALLATION BY SELF FLOW CASTING. ITS HIGH THERMAL CONDUCTIVITY MAKES IT IDEAL FOR APPLICATIONS WHERE HIGH HEAT TRANSFER IS IMPORTANT. SUREFLOW 80 SC SHOWS EXCELLENT RESISTANCE TO ABRASION, THERMAL SPALLING AND CORROSION,*

THE DATA SHOWN IS BASED ON MATERIAL PREPARED TO A SELF FLOWING CONSISTANCY AND POURED INTO FORMWORK WITHOUT VIBRATION OR TAMPING.

MAXIMUM SERVICE TEMPERATURE (M.S.T.) 1500°C

<u>BULK DENSITY</u>					<u>TYPICAL</u>
					<u>(METRIC)</u>
@ 110°C	160 - 165	LBS/FT <sup>3</sup>	2560 - 2640	KG/M <sup>3</sup>	(2610)
@ 815°C	155 - 160	LBS/FT <sup>3</sup>	2480 - 2560	KG/M <sup>3</sup>	(2530)

<u>COLD CRUSHING STRENGTH</u>					
@ 815°C	10000 - 15000	P.S.I.	690 - 1035	KG/CM <sup>2</sup>	(800)

<u>PERMANENT LINEAR CHANGE</u>					
@ 815°C	- 0.00 TO - 0.40 %				(-0.28)

<u>CONDUCTIVITY OR "K" FACTOR</u>		
<u>MEAN TEMP</u>	<u>BTU/FT<sup>2</sup>/Hr/°F/in</u>	<u>W/mK</u>
@ 540°C	75.0	10.8

The properties shown on this data sheet represent typical average results generated using standard ASTM test methods (unless otherwise noted) conducted under controlled conditions and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice. RESCO PRODUCTS disclaims any expressed or implied warranties based on this sheet. 01/08/13 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet