



Product Data

Brand Name: CM95-35

Preparation

Method : Crushing and Screening of Selective Dead Burned Magnesite

Manufacturing Resco Canada, Inc.

Location : 1330 Route 148
Grenville-sur-la Rouge, Quebec
Canada
J0V 1B0

Bulk Density (pcf) : 135 2.16 (g/cm³)

Typical Chemical Analysis (%)

Magnesia (MgO)	95.1
Alumina (Al ₂ O ₃)	0.4
Silica (SiO ₂)	1.7
Iron Oxide (Fe ₂ O ₃)	1.0
Lime (CaO)	1.8

Typical Particle Size Analysis (% Retained) :

+20 mesh	1.0	(max)
-20 + 325	84.0	
Pan	15.0	

Standard Packaging: 55 lb. bags

Brand Code: 0781

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

01/25/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505