



PRODUCT DATA

Brand Name: EZ EST 60G

Description: EZ EST 60G is a cement-free, 60% alumina gun mix that can be installed by conventional gunning methods. This product requires an additional liquid binder, called EZ ADD binder, for installation. EZ ADD binder is added at the gunning nozzle during installation.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 3000°F (1650°C)

<u>Bulk Density (pcf)</u>	<u>Gunned Data</u>	
	After 220°F (105°C)	146
After 1500°F (815°C)	146	(2.34 g/cm ³)

<u>Cold Crushing Strength (psi)</u>		
After 1500°F (815°C)	6000	(420 kg/cm ²)

<u>Permanent Linear Change (%)</u>	
After 1500°F (815°C)	0.0 to -0.2

<u>Thermal Conductivity (K Factor)</u>	<u>BTU/ft²/hr./°F/inch</u>	<u>W/mK</u>
Mean Temperature		
1000°F (538°C)	4.1	0.59
1500°F (815°C)	4.2	0.60
2000°F (1093°C)	4.8	0.69

<u>Abrasion Loss (using ASTM C-704 Method)</u>		
After 1500°F (815°C)	10 cc	(Typical)

<u>Typical Chemical Analysis (%)</u>	
(Calcined Basis including Liquid Binder)	
Alumina (Al ₂ O ₃)	57.7
Silica (SiO ₂)	39.1
Iron Oxide (Fe ₂ O ₃)	0.8
Titania (TiO ₂)	2.0
Lime (CaO)	0.1
Magnesia (MgO)	0.2
Alkalis (Na ₂ O+K ₂ O)	0.1

Standard Packaging: 55 lb bag. 72 bags per pallet. Bulk packaging available.
Binder: 55 gallon drum, 265 gallon plastic totes

Brand Code: 4393 (Brand Code for EZ ADD Liquid is 8869)

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

01/03/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.