

## PRODUCT DATA

Brand Name: Description:

## LADLELOCK 80

tion: LADLE LOCK 80 IS A HIGH ALUMINA, AIR SETTING MORTAR, PREMIXED. AVAILABLE CONSISTENCIES: DIPPING, TROWELLING (Winterized Versions Available)

Physical properties shown are average values of samples taken under controlled conditions ASTM test methods used where applicable

Maximum Service Temperature: 3200°F (1760°C)

Material Installed Weight (psi)	140	2.24 (g/cm <sup>3</sup> )
Moisture Loss on Drying	16.40%	
Maximum Grain Size	48 Mesh	
Cold Modulus of Rupture (psi)		
After 300°F (149°C)	400 - 600	(28 - 42 kg/cm <sup>2</sup> )

**Typical Chemical Analysis (%)** 

(Calcined Basis)	
Alumina (Al <sub>2</sub> O <sub>3</sub> )	79.2
Silica (SiO <sub>2</sub> )	14.2
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> )	1.2
Titania (TiO <sub>2</sub> )	3.2
Lime (CaO)	0.2
Magnesia (MgO)	0.1
Alkalis (Na <sub>2</sub> O+K <sub>2</sub> O)	2.0

## Standard Packaging: 50 lb. plastic pail

Brand Code: 3081 (Dip) 3083 (Trowel)

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed speci fications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the r ight to modify the properties and specifications at any time without prior notice.

**RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.** 

01/20/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determ ine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505