



PRODUCT DATA

Brand Name: LARCOBOND®
Description: LARCOBOND is a dry, heat-setting, chrome ore-containing mortar that has good workability and water retention. This mortar is suitable for dipping and trowelling.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Typical Water Required for Mixing (by weight):
Troweling..... 19.0%

Dry Material Required:
Use 440-490 pounds (200-225 kg) of dry mortar per 1000 9" x 4½" x 2½" (228mm x 114mm x 64mm) brick for a 1/16" (1.6mm) troweled joint.

Typical Chemical Analysis (%)
(Calcined Basis)

Magnesia (MgO)	55.7
Silica (SiO ₂)	5.1
Iron Oxide (Fe ₂ O ₃)	11.2
Alumina (Al ₂ O ₃)	8.3
Lime (CaO)	0.8
Titania (TiO ₂)	0.1
Chromic Oxide (Cr ₂ O ₃)	18.8

Standard Packaging: 55 lb. (25 kg) bag. 72 bags per pallet.

Brand Code: 0967

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

12/10/19 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.