

## PRODUCT DATA

LHV-124 **Brand Name:** 

Description: LHV-124 is a lumnite, haydite, and vermiculite (LHV) mix. It is a lightweight, 60 pcf insulating castable that can be installed by

casting and pneumatic gunning methods.

Physical properties shown are average values of samples taken under controlled conditions

ASTM test methods used where applicable

Maximum Service Temperature: 2000°F (1093°C)

Dry Material Required per Cubic Foot: 60 lbs. (approximate)

Typical Water Required for Mixing (by weight):

Casting ..... 44.0%

Bulk Density (pcf)	Cast Data		Gunning Data	
After 1500°F (815°C)	60	(0.96 g/cm <sup>3</sup> )	66	(1.06 g/cm <sup>3</sup> )
Cold Crushing Strength (psi)				
After 1500°F (815°C)	400	(28 kg/cm <sup>2</sup> )	440	(31 kg/cm <sup>2</sup> )
Permanent Linear Change (%)				
After 1500°F (815°C)	-0.4 to 0.0		-0.4 to 0.0	
Thermal Conductivity (K Factor)				
Mean Temperature	BTU/ft <sup>2</sup> /hr./°F/inch	<u>W/mK</u>		
1000°F (540°C)	1.6	0.23		
1500°F (815°C)	1.8	0.26		
2000°F (1093°C)	2.2	0.32		
Typical Chemical Analysis (%)				
(Calcined Basis)				
Alumina (Al <sub>2</sub> O <sub>3</sub> )	31.6			
Silica (SiO <sub>2</sub> )	46.9			
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> )	3.5			
Titania (TiO <sub>2</sub> )	1.1			
Lime (CaO)	14.3			
Magnesia (MgO)	1.6			
Alkalis (Na <sub>2</sub> O+K <sub>2</sub> O)	1.0			

Standard Packaging: 50 lb bag. 50 bags per pallet. Bulk packaging available.

Brand Code:

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

09/08/2020 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505