



# PRODUCT DATA

Brand Name: **MULTERM 880**

Physical properties shown are average values of samples taken under controlled conditions  
ASTM test methods used where applicable

Maximum Service Temperature: 3272°F (1800°C)

**Bulk Density (pcf)**

As Received 171 - 178 (2.75 - 2.85 g/cm<sup>3</sup>)

**Modulus of Rupture (psi)**

At 70°F (21°C) 1300 - 1880 (91 - 132 kg/cm<sup>2</sup>)

**Cold Crushing Strength (psi)**

At 70°F (21°C) 6080 - 8980 (426 - 629 kg/cm<sup>2</sup>)

**Apparent Porosity (%)**

As Received 18 - 22

**Thermal Conductivity (K Factor)**

Mean Temperature	<u>BTU/ft<sup>2</sup>/hr./°F/inch</u>	<u>W/mK</u>
2200°F (1200°C)	12.9	1.86

**Typical Chemical Analysis (%)**

(Calcined Basis)

Alumina (Al <sub>2</sub> O <sub>3</sub> ) .....	88.0
Silica (SiO <sub>2</sub> ) .....	10.0
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ) .....	0.5
Titania (TiO <sub>2</sub> ) .....	0.5
Alkalines (CaO+MgO) .....	0.5
Alkalis (Na <sub>2</sub> O+K <sub>2</sub> O) .....	0.5

Brand Code: 2803

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/16/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.