

PRODUCT DATA

Brand Name:	NULINE 20 I	NULINE 20 NF (TL 0741)		
Description:	RESIN BONDED, MAG	RESIN BONDED, MAGNESIA-CARBON BRICK Fused Grain		
	erties shown are averages based on thods used where applicable	standard brid	ck sizes.	
Bulk Density	<u>(pcf)</u>			
	As Received	178	(2.85 g/cm ³)	
	After Coking	174	(2.79 g/cm ³)	
<u>Modulus of R</u>	<u>Rupture (psi)</u>			
	At 70°F (21°C)	2000	(140 kg/cm ²)	
Coked Poros	<u>ity (%)</u>			
	After Coking	10.9		
Total Carbon				
	After Coking	19.3		
Typical Chem	nical Analysis (%)			
(Calcined Basis	•			
	Magnesia (MgO)	96.3		
	Silica (SiO ₂)	1.0		
	Alumina (Al ₂ O ₃)	0.2		
	Lime (CaO)	2.0		
	Iron Oxide (Fe ₂ O ₃)	0.5		
Brand Cada	7400			

Brand Code: 7422

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

01/24/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505