

Product Data

Brand : PYROPHYL® SERIES

Preparation

Method: Crushing and Screening of Selective Mined High Andalusite Ores

Manufacturing Piedmont Minerals Division

Location: Post Office Box 566; 231 Piedmont Drive

Hillsborough, NC 27278

| Typical Chemical Analysis (%) | | R-1403 | R-2253 |
|---|--|--------|--------|
| Alumina (Al ₂ O ₃) | | 21.0 | 20.0 |
| Silica (SiO ₂) | | 74.7 | 75.7 |
| Iron Oxide (Fe ₂ O ₃) | | 0.7 | 0.7 |
| Titania (TiO ₂) | | 0.4 | 0.4 |
| Alkalis (Na ₂ O+K ₂ O) | | 0.4 | 0.4 |
| Other | | 2.8 | 2.8 |
| Typical Particle Size Analysis (% Retained) : | | | |
| +200 mesh | | 12.0 | 1.0 |
| -200 mesh | | 88.0 | 99.0 |
| Bulk Density (pcf) : | | 60 | 55 |
| Pyrometric Cone Equivalent (ASTM C-24): | | 29 | 26 |

Standard Packaging: 50 lb. bags. 60 bags per pallet/ Super Sacks/ Bulk Trucks and Rail Cars

Brand Code: 0261 0263

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet. 03/03/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505