

## **Product Data**

Preparation Method :	Crushing and Screening of Selective Mined High Andalusite Ores			
Manufacturing Location :	Piedmont Minerals Division Post Office Box 566; 231 Piedmont Drive Hillsborough, NC 27278			
Typical Chemical Analysis (%)		<u>2253</u>	<u>2254</u>	<u>3503</u>
	Alumina (Al <sub>2</sub> O <sub>3</sub> )	20.5	20.0	20.5
	Silica (SiO <sub>2</sub> )	75.5	75.0	75.5
	Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> )	0.4	0.6	0.4
	Titania (TiO <sub>2</sub> )	0.4	0.0	0.4
	Alkalis (Na <sub>2</sub> O+K <sub>2</sub> O)	0.4	0.4	0.4
	Other	2.8	4.0	2.8
Typical Particle	e Size Analysis (% Retained) :			
	+200 mesh	1.0	1.0	0.0
	-200 mesh	99.0	99.0	100 (99% -325 me
Bulk Density (pcf) :		45	45	40
Pyrometric Cone Equivalent (ASTM C-24) :		26	26	26
0.000				
Standard Pack	<b>aging:</b> 50 lb. bags. 60 bags per palle	t Super Sack	S/ BUIK I rucks	and Kall Cars
Brand Code:		0268	0723	0269

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet. 03/03/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

reserves the right to modify the properties and specifications at any time without prior notice.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505