



# PRODUCT DATA

**Brand Name:** QUIKLITE 9LI-DS

**Description:** QUIKLITE 9LI-DS is a dust suppressed, medium weight, insulating castable that can be installed by casting or conventional gunning methods. This castable features a reduced dust level, high strength, and a low iron content. After the initial set, QUIKLITE 9LI-DS can be initially heated without using the traditional ramp-and-hold heatup schedule. Use the recommended QUIKTURN heatup schedule for the initial heatup.

Physical properties shown are average values of samples taken under controlled conditions  
ASTM test methods used where applicable

**Maximum Service Temperature: 2600°F (1427°C)**

**Typical Water Required for Mixing (by weight) :**

Casting ..... 24%  
Predampening for Gunning ..... 8.3 to 10.4%

	Casting Data		Gunned Data	
<b>Bulk Density (pcf)</b>				
After 1500°F (815°C)	85	(1.36 g/cm <sup>3</sup> )	95	(1.52 g/cm <sup>3</sup> )
<b>Cold Crushing Strength (psi)</b>				
After 1500°F (815°C)	1300	(91 kg/cm <sup>2</sup> )	1500	(105 kg/cm <sup>2</sup> )
<b>Apparent Porosity (%)</b>				
After 1500°F (815°C)	45.0%		40.0%	
<b>Thermal Conductivity (K Factor)</b>	<u>BTU/ft<sup>2</sup>/hr./°F/inch</u>	<u>W/mK</u>	<u>BTU/ft<sup>2</sup>/hr./°F/inch</u>	<u>W/mK</u>
500°F (260°C)	3.8	0.55	4.4	0.64
1000°F (538°C)	3.3	0.48	3.9	0.57
1500°F (815°C)	3.6	0.52	4.2	0.61
<b>Permanent Linear Change (%)</b>				
Green to 1500°F (815°C)	-0.4 to 0.0		-0.4 to 0.0	
220°F (105°C) to 1500°F (815°C)	-0.3 to 0.0		-0.3 to 0.0	

**Typical Chemical Analysis (%)**

(Calcined Basis)

Alumina (Al <sub>2</sub> O <sub>3</sub> ) .....	39.2
Silica (SiO <sub>2</sub> ) .....	44.4
Lime (CaO) .....	12.4
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ) .....	1.0
Titania (TiO <sub>2</sub> ) .....	1.7
Magnesia (MgO) .....	0.3
Alkalies (Na <sub>2</sub> O+K <sub>2</sub> O) .....	1.0

**Standard Packaging:** 50 lb bag. 50 bags per pallet. Bulk packaging available.

Brand Code: 1613

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

03/06/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.