



PRODUCT DATA

Brand Name:

REF RAM 70 IH

Description: Phosphate bonded, high alumina plastic with improved corrosion resistance in the matrix. Good workability, excellent strength and volume stability over a wide temperature range.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 3000°F (1650°C)

Bulk Density (pcf)

After 250°F (121°C)	165	(2.64 g/cm ³)
---------------------	-----	---------------------------

Modulus of Rupture (psi)

After 250°F (121°C)	1000	(70 kg/cm ²)
After 1500°F (815°C)	1250	(88 kg/cm ²)
After 2500°F (1371°C)	1200	(84 kg/cm ²)

Permanent Linear Change (%)

After 250°F (121°C)	-0.2
After 1000°F (538°C)	-0.3
After 2500°F (1371°C)	0.5

Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al ₂ O ₃)	61.5
Silica (SiO ₂)	32.5
Iron Oxide (Fe ₂ O ₃)	0.6
Titania (TiO ₂)	0.7
Phosphorus Pentoxide (P ₂ O ₅)	3.5
Other	1.2

Brand Code: 2443

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

03/09/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505