

PRODUCT DATA

Brand Name: RESCOBOND LW 78G TL0938

Description: RESCOBOND LW 78G is a chemically-bonded, air-setting, single component medium weight

gunning mix. This product can be installed by conventional gunning and handpacking methods and bonds to existing refractory. When gunning, predampening is NOT suggested for this gun mix. This product develops a quick set and can be heated shortly after installation. RESCOBOND LW 78G

should NOT be installed by vibration casting methods.

Physical properties shown are average values of samples taken under controlled conditions ASTM test methods used where applicable

Maximum Service Temperature: 3000°F (1650°C)

_	Gunned Data	
Bulk Density (pcf)		
After 1500°F (815°C)	175	(2.80 g/cm ³)
Cold Crushing Strength (psi)		
After 1500°F (815°C)	4500	(315 kg/cm ²)
Modulus of Rupture (psi)		
After 1500°F (815°C)	1350	(94 kg/cm ²)
Abrasion Loss (using ASTM C-704 Method)		
After 1500°F (815°C)	Less than 13 cc	
Typical Chemical Analysis (%)		
(Calcined Basis)		
Alumina (Al ₂ O ₃)	28.9	
Silica (SiO ₂)	49.7	
Iron Oxide (Fe ₂ O ₃)	2.3	
Titania (TiO ₂)	0.8	
Lime + Magnesia (CaO+MgO)	8.8	
Alkalies (Na ₂ O+K ₂ O)	0.6	

Standard Packaging: 50 lb bag. 50 bags per pallet. Bulk packaging available.

Brand Code: 8977

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

8.9

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

Phosphorus Pentoxide (P₂O₅)

03/13/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505