

PRODUCT DATA

Brand Name: RESCORAM 90

Description: RESCORAM 90 is a high alumina, phosphate-bonded plastic material that is used throughout the metals,

power, cement, and lime producing industries. Its chemical bond develops high strength at lower temperatures. This property makes it ideal for application where there is insufficient heat to develop the

ceramic bond required in heat-setting plastics.

Physical properties shown are average values of samples taken under controlled conditions ASTM test methods used where applicable

Maximum Service Temperature: 3100°F (1704°C)

	Ramming Data	
Bulk Density (pcf)		
As Received	192	(3.07 g/cm ³)
Modulus of Rupture (psi)		
After 1500°F (815°C)	2400	(168 kg/cm ²)
Thermal Conductivity (K Factor)		
Mean Temperature	BTU/ft ² /hr./°F/inch	W/mK
1000°F (540°C)	13.5	1.95
1500°F (815°C)	12.8	1.84
2000°F (1093°C)	13.3	1.92
Permanent Linear Change (%)		
After 1500°F (815°C)	-0.02	
Abrasion Loss (using ASTM C-704 Method)		
After 1500°F (815°C)	Less than 5 cc	
Typical Chemical Analysis (%)		
(Calcined Basis)		
Alumina (Al ₂ O ₃)	93.8	
Silica (SiO ₂)	2.6	
Iron Oxide (Fe ₂ O ₃)	0.2	
Lime (CaO)	0.1	
Magnesia (MgO)	0.1	
Phosphorus Pentoxide (P ₂ O ₅)	3.0	
Alkalies (Na ₂ O+K ₂ O)	0.3	

Standard Packaging: 55 lb carton. 64 cartons per pallet

Brand Code: 0500

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

03/27/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505