



PRODUCT DATA

Brand Name: **SICTERM 880**

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 3000°F (1650°C)

Bulk Density (pcf)

As Received 156 - 163 (2.50 - 2.60 g/cm³)

Modulus of Rupture (psi)

At 70°F (21°C) 2450 - 3625 (172 - 254 kg/cm²)

Cold Crushing Strength (psi)

At 70°F (21°C) 13000 - 19000 (910 - 1330 kg/cm²)

Apparent Porosity (%)

As Received 15 - 19

Thermal Conductivity (K Factor)

Mean Temperature	<u>BTU/ft²/hr./°F/inch</u>	<u>W/mK</u>
2200°F (1200°C)	108.9	15.7

Typical Chemical Analysis (%)

(Calcined Basis)

Silicon Carbide (SiC)	90.0
Silica (SiO ₂)	8.0
Iron Oxide (Fe ₂ O ₃)	1.0
Alumina (Al ₂ O ₃)	1.0

Brand Code: 2806

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESKO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/17/17 is the date that this data sheet was updated. Check with your RESKO sales representative or RESKO website to determine you have the current sheet.