

PRODUCT DATA

Brand Name: SLURRY COAT

Description: SLURRY COAT is a fireclay based refractory coating used for prevention of slag pot

stickers. SLURRY COAT is shipped pre-mixed and ready to apply. SLURRY COAT is

available in standard and winterized versions.

Physical properties shown are average values of samples taken under controlled conditions ASTM test methods used where applicable

Maximum Service Temperature: 2600°F (1427°C)

Moisture Loss on Drying (%): 50%

Material Weight per Gallon: 11.9 - 12.1 lbs.

Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al ₂ O ₃)	27.1
Silica (SiO ₂)	68.3
Iron Oxide (Fe ₂ O ₃)	1.6
Titania (TiO ₂)	1.1
Lime (CaO)	0.6
Magnesia (MgO)	1.4
Alkalis (Na ₂ O+K ₂ O)	0.2

Brand Code: 3278 3281 (Winterized)

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/13/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determ ine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505